


Tarastep Premium				
			Brazilia	Indiana
DESCRIPTION				
Total thickness	EN 428	mm	3.30	3.40
Thickness of wearlayer	EN 429	mm	1.00	0.96
Weight	EN 430	g/m ²	2850	3175
Width of sheet	EN 426	cm	100	100
Length of sheet	EN 426	lm	22	22
CLASSIFICATION				
Norm / product specification	-	-	EN 651	EN 651
European classification	EN 685	class	34-42	34-42
Fire rating	EN 13 501 - 1	class	C _{fl} -s1	C _{fl} -s1
Static electrical charge	EN 1815	kV	< 2	< 2
PERFORMANCE				
Wear resistance	EN 660.1	mm	≤ 0.08	≤ 0.08
Wear group	EN 651	group	T	T
Dimensional stability	EN 434	%	≤ 0.4	≤ 0.4
Residual indentation	EN 433	mm	≤ 0.2	≤ 0.2
Impact sound insulation	EN ISO 717-2	dB	16	16
Thermal conductivity	EN 12 524	W/(m.K)	0.25	0.25
Colour fastness	EN 20 105-B02	-	≥ 6	≥ 6
Chemical products resistance	EN 423	-	good	good
Anti bacterial and fungicidal treatment	-	-	Sanosol®	Sanosol®
Surface treatment	-	-	-	-
CE MARKING				
	EN 14041		