


			TARASTEP INITIAL
<b>DESCRIPTION</b>			
Total thickness	EN 428	mm	3,85
Thickness of wearlayer	EN 429	mm	0,85
Weight	EN 430	g/m <sup>2</sup>	3340
Width of sheet	EN 426	cm	101
Length of sheet	EN 426	lm	22
Tile size	EN 427	mm	
Number of tiles per package	-	-	
<b>CLASSIFICATION</b>			
Norm / Product specification			EN 651
European classification	EN 685	class	34 - 42
Fire rating	EN 13 501-1	class	C <sub>f</sub> s1
Static electrical propensity	EN 1815	kV	< 2
Slip resistance wet: ramp test with oil	DIN 51130	class	R9
<b>PERFORMANCE</b>			
Wear resistance	EN 660.1	mm	≤ 0,08
Wear group	EN 651	-	T
Dimensional stability	EN 434	%	≤ 0,40
Residual indentation	EN 433	mm	≤ 0,20
Impact sound insulation	EN ISO 717-2	dB	18
Thermal conductivity	EN 12 524	W/(m.K)	0,25
Colour fastness	EN 20 105 - B02	degree	≥ 6
Chemical products resistance	EN 423	-	OK
Anti-bacterial and fungicidal treatment	-	-	Sanosol®
Surface treatment	-	-	
<b>MARQUAGE CE</b>			
	EN 14041		