


			Tarasafe		
			Standard	Iona	Super
DESCRIPTION					
Total thickness	EN 428	mm	2.00	2.00	2.20
Thickness of wearlayer	EN 429	mm	≥0.9	1.14	1.14
Weight	EN 430	g/m ²	2 260	2 650	2 900
Width of sheet	EN 426	cm	200	200	200
Length of sheet	EN 426	lm	20	20	20
CLASSIFICATION					
Norm			EN 649	EN 649	EN 649
European classification	EN 685	class	34 - 43	34 - 43	34 - 43
K rating		class	K5	K5	K5
Fire rating	EN 13501-1	class	B _{fl} -s1	B _{fl} -s1	B _{fl} -s1
Static electrical propensity	EN 1815	kV	< 2	< 2	< 2
RRL pendulum test (wet test)	BS 7976	°	≥ 36	≥ 36	≥ 36
Surface roughness R _{tm}		µm	≥ 20	≥ 20	≥ 20
Slip resistance wet	DIN 51 130	class	R10	R10	R10
PERFORMANCE					
Wear resistance	EN 660.1	mm	≤0.08	≤0.08	≤0.08
Wear group			T	T	T
Dimensional stability	EN 434	%	≤0.40	≤0.40	≤0.40
Residual indentation	EN 433	mm	≤0.10	≤0.10	≤0.10
Impact sound insulation	EN ISO 717-2	dB			
Thermal conductivity	EN 12 524	W/(m.K)	» 0.25	» 0.25	» 0.25
Colour fastness	EN 20 105 B02	degree	≥6	≥6	≥6
Chemical products resistance	EN 423		good	good	good
Anti-bacterial and fungicidal treatment			Sanosol®	Sanosol®	Sanosol®
Surface treatment					
CE MARKING					
	EN 14041		