

<b>DESCRIPTION</b>			
Total thickness	EN ISO 24346	mm	2.00
Thickness of wearlayer	EN ISO 24340	mm	0.80
Weight	EN ISO 23997	g/m <sup>2</sup>	2435
Width of sheet	EN ISO24341	cm	200
Length of sheet	EN ISO24341	ml	20
<b>CLASSIFICATION</b>			
Norm / Product specification	-	-	EN ISO 10582
European classification	EN ISO 10874	class	34 - 43
Fire rating	EN 13 501-1	class	Bfl-s1
Static electrical propensity	EN 1815	kV	< 2
Slip resistance : pendulum test (dry and wet)	BS 7976-2	PTV	> 36
Surface roughness	-	µm	Rz ≥ 20
Slip resistance : ramp test + oil – footwear	DIN 51130	class	R10
Slip resistance : ramp test + water – barefoot	DIN 51097	class	B
Slip resistance – footwear and barefoot + water	EN 13845-annexe C	class	Esf – Esb
Water tightness in special wet area	EN 13553	-	OK
<b>PERFORMANCES</b>			
Wear resistance	EN 660.2	mm <sup>3</sup>	≤ 2.0
Wear group	-	group	T
Type Binder content	EN ISO 10582	type	I
Dimensional stability	EN ISO 23999	%	≤ 0.40
Residual indentation (exigency)	EN ISO 24343-1	mm	≤ 0.10
Residual indentation (average measured value)	-	mm	~ 0.03
Thermal conductivity	EN ISO 10456	W/(m.K)	0.25
Colour fastness	EN 20 105 - B02	degré	≥ 6
Surface treatment	-	-	SparClean®
Chemical products resistance	EN ISO 26987	-	OK
Anti-bacterial activity (MRSA) (1)	ISO 22196	-	> 99% inhibits growth
<b>ENVIRONMENT / INDOOR AIR QUALITY</b>			
TVOC after 28 days	ISO 16000-6	µg/ m <sup>3</sup>	< 100

(1) The implementation of an effective cleaning regime is the best defence against infection.