

DESCRIPTION

Total thickness	EN ISO24346	mm	1.30
Wearlayer thickness	EN ISO24340	mm	0.15
Poids	EN ISO 23997	g/m ²	1105
Weight	EN ISO 24341	cm	200 / 300 / 400
Width of sheet	EN ISO 24341	ml	≈ 35

CLASSIFICATION

Norm / Product specification	-	-	EN ISO 26986
European classification	EN ISO 10874	class	21
Impact sound insulation	EN ISO 717-2	dB	10
Fire rating	EN 13 501-1	class	Bfls1
Static electrical propensity	EN 1815	kV	< 2
Slip resistance wet : ramp test with oil	DIN 51130	class	-





PERFORMANCE

Wear group	-	group	T
Dimensional stability (requirement)	EN ISO 23999	%	-
Dimensional stability (average measured value)	-	%	-
Residual indentation (requirement)	EN ISO 24343-2	mm	≤ 0.35
Residual indentation (average value measured)		mm	-
Thermal conductivity	EN ISO 10456	W/(m.K)	0.25
Colour fastness	EN 20 105 - B02	degree	≥ 6
Surface treatment	-	-	Diamalite
Chemical products resistance	EN ISO 26987	class	ok

ENVIRONMENT / INDOOR AIR QUALITY

TVOC after 28 days	ISO 16000-6	µg/ m ³	< 100
Certification	-	-	-

MARQUAGE CE

	EN 14041	-	  
		-	