




	TARASTEP PRO		
DESCRIPTION			
Total thickness	EN ISO 24346	mm	3.45
Wearlayer thickness	EN ISO 24340	mm	1.00
Weight	EN ISO 23997	g/sq.m	3005
Width of sheet	EN ISO 24341	cm	100
Length of sheet	EN ISO 24341	lm	20
CLASSIFICATION			
Norm / Product specification	-	-	EN ISO 11638
European classification	EN ISO 10874	class	34 - 42
Fire rating	EN 13501-1	class	B _{fl} -s1
Static electrical propensity	EN 1815	kV	< 2
Slip resistance wet : ramp test with oil	DIN 51130	class	R10
PERFORMANCE			
Wear resistance	EN 660.2	mm ³	≤ 2.0
Wear group	NF189	group	T
Dimensional stability (requirement)	EN ISO 23999	%	≤ 0.40
Residual indentation (requirement)	EN ISO 24343-1	mm	≤ 0.20
Residual indentation (average value measured)	-	mm	0.10
Impact sound insulation	EN ISO 717-2	dB	17
Thermal conductivity	EN ISO 10456	W/(m.K)	0.25
Colour fastness	EN 20 105 - B02	degree	≥ 6
Surface treatment	-	-	Protecsol®
Chemical products resistance	EN ISO 26987	-	OK
Anti-bacterial activity (E. coli - S. aureus - MRSA) (1)	ISO 22196	-	> 99 % Inhibits growth
Antiviral activity (human coronavirus 229E) (1)	ISO 21702	-	> 99,3% after 2h
ENVIRONMENT / INDOOR AIR QUALITY			
TVOC after 28 days	ISO 16000-6	µg/ m ³	< 100
Certification	-	-	Floorscore®
CE MARKING			
	EN 14041	-	  
		-	

(1) The implementation of an effective cleaning regime is the best defence against infection