

**DESCRIPTION**

Total thickness	EN 428	mm	4.00
	ASTM F386	inch	0.16
Thickness of wearlayer	EN 429	mm	0.30
	ASTM F410	inch	0.01
Weight	EN 430	g/m <sup>2</sup>	7600
Size	EN 427	cm	30.5 x 61 / 18.4 x 121.9
	ASTM F 536	inch	12"x24" / 7,25"x48"
Number of tiles per package	-	-	10
Number of planks per package	-	-	8

**CLASSIFICATION**

Norm / Product specification	-	-	EN 649
	ASTM F 1700		
European classification	EN 685	class	23 - 31
Fire rating	EN 13 501-1	class	B <sub>fl</sub> -s1
Static electrical propensity	EN 1815	kV	< 2
Slip resistance wet : ramp test oil	DIN 51 130	class	R9-R10-R11*




**PERFORMANCE**

Wear Resistance	EN 660.2	mm <sup>3</sup>	≤ 2.0
Wear Group	EN 649	-	T
Type Binder content	ISO 10582	type	I
Room Impact	NF S 31074	dB	74
Impact sound insulation	EN ISO 717-2	dB	5
Dimensional stability	EN 434	%	≤ 0.15
Residual indentation	EN 433	mm	≤ 0.10
Castor chair test (type W)	EN 425	-	OK
Thermal conductivity	EN 12 524	W/(m.K)	0.25
Colour fastness	EN 20 105 - B02	degree	≥ 6
Surface treatment	-	-	PUR+
Chemical products resistance	EN 423	-	OK

**ENVIRONMENT / INDOOR QUALITY AIR**

TVOC after 28 days	ISO 16000-6	µg/ m <sup>3</sup>	< 100
--------------------	-------------	--------------------	-------

**MARQUAGE CE**

	EN 14041		
			

\*Grain/Emboss/Prägung/Embossing/Grabado/Relevo/Goffratura :  
Saw effect / Natural = R9  
Brushed / Rustic wood / Hammered = R10  
Perforated = R11