

**DESCRIPTION**

Total thickness	EN 428	mm	2.50
	ASTM F386-02	inch	0.1
Thickness of wearlayer	EN 429	mm	0.70
	ASTM F410-02	inch	0.028
Weight	EN 430	g/m <sup>2</sup>	4395
Tile size	EN 427	mm	
	ASTM F 536	inch	-
Plank size	EN 427	mm	228 X 914 - 152 X 914 - 706 X 914
	ASTM F 536	inch	3" x 36" - 6" x 36" - 9" x 36"
Number of tiles per package	-	-	
Number of planks per package	-	-	24
Coverage / box	-	sq.m	3.34
	-	sq.ft.	35.95





**CLASSIFICATION**

Norm / Product specification	-	-	EN 649
	ASTM F 1700- 04	-	Class III Type B
European classification	EN 685	class	34 - 43
Fire rating	EN 13 501-1	class	Bfl-s1
	ASTM E648-08	class	class I
	CAN/ULC S102.2	-	tested in accordance
Static electrical propensity	EN 1815	kV	< 2
Slip resistance wet: ramp test with oil	DIN 51 130	class	R9

**PERFORMANCE**

Wear resistance	EN 660.2	mm <sup>3</sup>	≤ 2.0
Wear group	EN 649	-	T
Dimensional stability	EN 434	%	≤ 0.15
Residual indentation	EN 433	mm	≤ 0.10
Thermal conductivity	EN 12524	W/(m.K)	0.25
Colour fastness	EN 20 105 - B02	degree	≥ 6
Chemical products resistance	EN 423	-	OK
Surface treatment	-	-	PUR+
TVOC after 28 days	ISO 16000-6	µg/ m <sup>3</sup>	< 100

**CE MARKING**

	EN 14041	-	  
		-	