

DESCRIPTION

Total thickness on grainside	EN ISO 24346 [EN 428]	mm	2.40
Thickness of wearlayer	EN ISO 24340 [EN 429]	mm	2.40
Weight	EN ISO 23997 [EN 430]	g/sq.m	3100
Width of sheet	EN ISO 24341 [EN 426]	cm	200
Length of sheet	EN ISO 24341 [EN 426]	lm	20

CLASSIFICATION

Norm / Product specification	-	-	EN ISO 10581 [EN 649]
European classification	EN ISO 10874 (EN 685)	class	34 - 43
Fire rating	EN 13501-1	class	B _{fl} -s1
Static electrical propensity	EN 1815	kV	< 2
Slip resistance wet : ramp test with oil	EN 16165:2021 – Appendix B (DIN 51 130)	class	R9
Slip resistance wet : barefoot	EN 16165:2021 – Appendix A (DIN 51097)	class	B
Water tightness	EN 13553	-	OK



PERFORMANCE

Wear resistance	EN 660.2	mm ³	≤ 4.0
Wear group	(EN 649)	-	P
Type Binder content	ISO 10581	type	I
Dimensional stability	EN ISO 23999 [EN 434]	%	≤ 0.40
Residual indentation (requirement)	EN ISO 24343-1 [EN 433]	mm	≤ 0.10
Residual indentation (measure)	-	mm	≈ 0.03
Thermal conductivity	EN ISO 10456 (EN12524)	W/(m.K)	0.25
Colour fastness	EN ISO 105 - B02	degree	≥ 6
Chemical products resistance	EN ISO 26987 [EN 423]	-	OK

ENVIRONMENT / INDOOR AIR QUALITY

TVOC after 28 days	ISO 16000-6	µg/ m ³	< 10
Certification	-	-	Floorscore®

CE MARKING

	EN 14041	-	
		-	