

DESCRIPTION

Total thickness	EN ISO 24346	mm	2.50
Thickness of wearlayer	EN ISO 24340	mm	1.02
Weight	EN ISO 23997	g/m ²	2660
Width of sheet	EN ISO 24341	cm	200
Length of sheet	EN ISO 24341	lm	20

CLASSIFICATION

Norm / Product specification	-	-	EN ISO 10582
European classification	EN ISO 10874	class	34 - 43
Fire rating	EN 13 501-1	class	Bfl-s1
Static electrical propensity	EN 1815	kV	< 2
Slip resistance wet : ramp test oil (1)	DIN 51 130	class	R10

PERFORMANCE

Wear Resistance	EN 660.2	mm ³	≤ 2.0
Wear Group	-	group	T
Type Binder content	EN ISO 10582	type	I
Dimensional stability	EN ISO 23999	%	≤ 0.40
Residual indentation (requirement)	EN ISO 24343-1	mm	≤ 0.10
Residual indentation (value)	-	mm	≈ 0.03
Impact sound insulation	EN ISO 717-2	dB	8
Castor chair test (type W)	ISO 4918	-	OK
Thermal conductivity	EN ISO 10456	W/(m.K)	0.25
Colour fastness	EN 20 105 - B02	degree	≥ 6
Surface treatment	-	-	Evercare™
Chemical products resistance (2)	EN ISO 26987	-	OK
Anti-bacterial activity (E.coli – S. aureus – MRSA) (3)	ISO 22196	-	> 99% inhibits growth
Anti-Viral activity (human coronavirus 229E) (3)	ISO 21702	-	> 99,7% after 2 hours

ENVIRONMENT / INDOOR QUALITY AIR

TVOC after 28 days	ISO 16000-6	µg/m ³	<10
Certification	-	-	Floorscore®

MARQUAGE CE

	EN 14041	  
		

- (1) For lifetime sustainable wet resistance, please refer to Tarasafe ranges.
 (2) Regarding the resistance to chemicals, please download the corresponding leaflet from our website
 (3) The implementation of an effective cleaning method is the best defence against infection.