

**DESCRIPTION**

Total thickness	EN 428	mm	3.35
	ASTM F386-02	inch	0.13
Wearlayer thickness	EN 429	mm	0,85
	ASTM F410-02	inch	0.03
Weight	EN 430	g/sq.m	3100
Width of sheet	EN 426	cm	101
	-	feet - inch	-
Length of sheet	EN 426	lm	20
	-	feet - inch	66'
Coverage / roll	-	sq.ft	0
	-	sq.m	0





**CLASSIFICATION**

Norm / Product specification	-	-	EN 651
	ASTM F1303-04	-	-
European classification	EN 685	class	34 - 42
Fire rating	EN 13 501-1	class	C <sub>fl</sub> -s1
	ASTM E648-08	class	
	CAN/ULC S102.2	-	-
Static electrical propensity	EN 1815	kV	< 2
Slip resistance wet : ramp test with oil	DIN 51 130	class	R9

**PERFORMANCE**

Wear resistance	EN 660.2	mm <sup>3</sup>	≤ 2.0
Wear group	EN 651	-	T
Dimensional stability	EN 434	%	≤ 0,40
Residual indentation (exigency)	EN 433	mm	≤ 0,20
Residual indentation (measure)	-	mm	0.11
Impact sound insulation	EN ISO 717-2	dB	17
Castor chair test (type W)	EN 425	-	OK
Thermal conductivity	EN 12 524	W/(m.K)	0.25
Colour fastness	EN 20 105 - B02	degree	≥ 6
Chemical products resistance	EN 423	-	OK
Treatment	-	-	Sanosol®
Surface treatment	-	-	
TVOC after 28 days	ISO 16000-6	µg/ m <sup>3</sup>	< 100

**CE MARKING**

	EN 14041	-	  
		-	