

EUROPEAN REACTION TO FIRE CLASSIFICATION REPORT ACCORDING TO THE EUROPEAN STANDARD EN 13501-1

Notified Body by the French State besides the European Commission under number : 0071

Product standard : NF EN 14041
Resilient, textile and laminate floorcoverings

(free translation of French classification report n°G031707 CEMATE/17)

N°G031707 - CEMATE/18

Material submitted by : GERFLOR
50 Cours de la République
69627 VILLEURBANNE Cedex
FRANCE

Commercial trademark : TARALAY / TARADAL CONFORT UNIS CONFORT 33 ET 43

Production site : GERFLOR TARARE
43 Boulevard Garibaldi
69170 TARARE
FRANCE

Brief description : Floorcovering in PVC

Date of report : 2006, June 23rd

**Only full reproduction of the present document is authorized.
It contains 4 pages**

1. INTRODUCTION

This classification report defines the classification assigned to product in accordance with the procedures given in EN 13501-1.

2. DETAILS OF CLASSIFIED PRODUCT

2.1. NATURE AND END USE APPLICATION

VSM type (NF EN 651 standard) floorcovering.

2.2. DESCRIPTION

Characteristics product :

Product	Thickness in mm	Mass per unit square meter in g/m ²
TARALAY / TARADAL CONFORT UNIS 33 ET 43	Wearing layer : 0.65 Calendered plasticized PVC Intercalary : 0.35 Coated PVC with reinforced glass grid Backing : 2.00 Chemical foam PVC Total thickness : 3.00 Tolerance : -0.15/+18	2300 Tolerance : -10/+13 %

Text report to be followed on next page

3. TEST REPORTS AND TEST RESULTS IN SUPPORT OF THIS CLASSIFICATION**3.1. TEST REPORTS**

Name of laboratory	Name of sponsor	Test report ref. n°	Test method
Laboratoire national de métrologie et d'essais 29 av. Roger Hennequin 78197 TRAPPES CEDEX	GERFLOR 50 Cours de la République 69627 VILLEURBANNE Cedex	File : G031707 CEMATE/16	Radiant panel EN ISO 9239-1

3.2. TEST RESULTS FOR FLOORINGS

Test method	Number of tests	Parameters	Results
EN ISO 9239-1 Glued to a particle board non-FR	4	Critical flux (kW/m ²) Smoke (%.min)	7.41 240

Text report to be followed on next page

4. CLASSIFICATION AND DIRECT FIELD APPLICATION

4.1. CLASSIFICATION

Fire behaviour	Smoke production	Flaming droplets
C_{fl}	s1	-

4.2. FIELD OF APPLICATION

This classification is valid for the product mentioned in § 2.2 or strictly and equally stipulated in the quoted production site.

Colour : various

Thickness : about 3.00 mm

Glued to wood substrate and A1 and A2 classified substrates

5. LIMITATIONS

5.1. RESTRICTIONS CONCERNING THE VALIDITY PERIOD OF THE CLASSIFICATION REPORT

None.

5.2. WARNING

This document does not represent type approval or certification of the product.

Trappes, the 23rd of June 2006

The Head of Fire Behaviour Division

Test Officer



Alain SAINRAT




Luc CHEVALIER